

**MANUFACTURER OF TECHNICAL AEROSOLS AND PRODUCTS FOR INDUSTRY
PROCESSES - MRO - MAINTENANCE
ALTERNATIVE SOLVENTS 100% SAFE**

Datasheet - Last update: 2025-02-12

**ANTI-SEIZE ALUMINIUM PASTE
GREASE FOR VERY HIGH TEMPERATURES
ASSEMBLY, INSTALLATION, REMOVAL
ENABLES RESOLUTION OF PITTING PROBLEMS
COMPLIES WITH SPECIFICATIONS
MIL A 907 ED - STM 7411 A
SECLF 216 - MIL A 907 E 80
iBiotec NEOLUBE® METAL 900**

DESCRIPTION

Facilitates assembly and enables disassembly of components and assemblies subjected to high temperatures or in an aggressive environment. Can be used and is effective when applied in a thin coat.

Excellent dynamic film-forming capacity.

Enables lifetime static surface treatment.

Product guaranteed free from metal salts, metalloids, or nitrites.

Lubricant and anti-corrosion agent for use at high temperatures.

Effective for static use and in the presence of vibrations.

Do not use on bearings or slow-moving rollers without frequently applying lubricant.

FIELDS OF USE

Screwed assemblies, including with the destruction of the thread geometry.

Steam connections. Cable glands. Mechanical seals.

Impregnation of sealing braids. Toric seals.

Sliding bearings on hot roll benders. Overheat gates.

Turbines. Combustion engines. Compressors. Gas generators. Foundry ejectors. Aluminium extrusion (start up before coating). Zamak stripping.

Curing mould seals. Furnace hinges.

Ingot clamps.

Bogie centre plates. Brake callipers.

Point welding machine jaws.

INSTRUCTIONS FOR USE

Shake the aerosol can vertically for a few moments after the ball in the can becomes detached. First degrease the mechanism to be lubricated as needed using Neutralène® V200 aerosol. Spray at a distance of 15 to 25 cm depending on the size of the mechanism.

TYPICAL PHYSICO-CHEMICAL PROPERTIES

PHYSICAL PROPERTIES OF THE GREASE			
PROPERTIES	STANDARD OR METHOD	VALUE	UNIT
Appearance	Visual	Paste	-
Colour	Visual	Aluminium	-
Apparent density at 25°C (pycnometer)	NF T 30 020	990	kg/m ³
NLGI Class	NLGI National Lubricating Grease Institute	2	Classification
Thickener	-	Inorganic	-
Solid lubricant content	-	Graphite/Aluminium	12%
Penetrability at 25°C Non-worked Worked, 60 strokes Worked, 1,000 strokes Worked, 10,000 strokes Worked, 100,000 strokes	NF ISO 2137 / ASTM 2176	265-295 265-295 265-295 275-305 275-305	1/10° mm 1/10° mm 1/10° mm 1/10° mm 1/10° mm
Dropping point Dropping point if greater than 360°C	NF ISO 2176 / ASTM D 566 ASTM D 2265	>250 -	°C
Impurities > 25 µm > 75 µm > 125 µm	FMTS 791 3005	nm nm nm	nb/ml nb/ml nb/ml

PHYSICO-CHEMICAL PROPERTIES OF THE BASE OIL

PROPERTIES	STANDARD OR METHOD	VALUE	UNIT
Characteristics of the base oil	-	Polymer	-
Kinematic viscosity at 40°C Kinematic viscosity at 100°C	NF EN ISO 3104	140 100	k k -q/Æ k k -q/Æ
Acid value (AV)	NF ISO 6618	0.38	mg KOH/l

PERFORMANCE PROPERTIES

PROPERTIES	STANDARD OR METHOD	VALUE	UNIT
Oil separation, 7 days at 40°C (bleeding)	NF T 60 191	0	% of mass
Oil separation, 24 hours at 41 kPa (bleeding under pressure)	ASTM D 1742	<2	% of mass
Sulphated ashes	NF T 60 144	1	% of mass
Copper strip corrosion	ASTM D 4048	1a	Rating
Hoffman oxidation	ASTM D 942	<10	psi
Loss by evaporation, 22 hours at 121°C	ASTM D 972	0	% of mass
Noack evaporation loss	NF T 60 101 CEC L-40 A-93 ASTM D5800	<0.5	% of mass
Elastomer swelling 70h at 212°F	ASTM D 4289.83	<0.8	Dimensional variation %
Static temperature ranges Continuous Peak	- -	-20 +900 -20 +1000	°C °C
Rotation factor	n.d _m	80,000	mm/min ⁻¹
4-ball test Wear scar diameter Wear load index	ASTM D 2266 / ISO 20 623	0.60 4000	mm daN
TIMKEN Test	ASTM D 2509	40	lbs

EMCOR rust-prevention test	NF T 60 135	0	Rating
Dynamic	ISO DP 6294/ ASTM D 1743	2	Rating
Static			
Resistance to water washout at 80°C	ASTM 1264	<1	% of mass

ADDITIONAL PROPERTIES

PROPERTIES	STANDARD OR METHOD	VALUE	UNIT
Tightening torque at 20°C	MIL A 907 E 80	80	Newton metres
Loosening torque at 450°C	MIL A 907 E 80	85	Newton metres
Loosening torque at 750°C	MIL A 907 E 80	100	Newton metres

* not measured or non-measurable

PRESENTATIONS



3% FIREPROFF PROPPELLANT

97% ACTIVE INGREDIENT

LAST 3 TIMES MORE
 Atmospheric gas of natural origin non-flammable
 Guaranteed without Butane Propane VOC highly inflammable
 Guaranteed without HFC greenhouse effect fluorinated gas
 Directive F.Gaz 5017.2014

Aerosol 650 ml





Tin 1 L



iBiotec® Tec Industries®Service
 Z.I La Massane - 13210 Saint-Rémy de Provence – France
 Tél. +33(0)4 90 92 74 70 – Fax. +33 (0)4 90 92 32 32
www.ibiotec.fr

USAGE RESERVE AUX UTILISATEURS PROFESSIONNELS
 Consulter la fiche de données de sécurité.

Les renseignements figurant sur ce document sont basés sur l'état actuel de nos connaissances relatives au produit concerné. Ils sont donnés de bonne foi. Les caractéristiques y figurant ne peuvent être en aucun cas considérées comme spécifications de vente. L'attention des utilisateurs est en outre attirée sur les risques éventuellement encourus lorsqu'un produit est utilisé à d'autres usages que ceux pour lequel il est conçu. Parallèlement, le client s'engagera à accepter nos conditions générales de marché de fournitures dans leur totalité, et plus particulièrement la garantie et clause limitative et exonératoire de Responsabilité. Ce document correspond à des secrets commerciaux et industriels qui sont la propriété de Tec Industries Service et, constituant un élément valorisé de son actif, ne saurait être communiqué à des tiers en vertu de la loi du 11 juillet 1979.